

Ethylene Vinyl Acetate Copolymer

SPECIFICATIONS

<u>PROPERTY</u>	<u>VALUE</u>	<u>UNITS</u>	<u>ASTM TEST METHOD</u>
Melt Index	1.8	g/10 min	D1238
Vinyl Acetate Incorporated	17	%	
Tensile Strength @ Break ²	2,100	%	D638
Elongation @ Break ²	730	%	D638
1% Secant Modulus	6,800	psi	D638
Dart Drop Impact Strength, F ₅₀ ³	>325	g	D1709
Low Temperature Brittleness	<-76	°C	D746
Vicat Softening Point	67	°C	D1525
Hardness, Shore A	90		D2240

NOTE: While the information herein is believed to be reliable and correct, nothing herein is intended and should not be construed as a representation or warranty, express or implied, as to results obtained or to be obtained by others who may make use of this information or with respect to the absence, existence or validity of patent rights, if any, of others involving any composition or process herein referred to; or an inducement or recommendation for the violation of any such patent rights, and responsibility and liability therefore is disclaimed.

B&F PLASTICS
INCORPORATED
www.bfplastics.com

540 N. 8 St., Richmond, IN 47374
765-962-6125, 800-562-8365
FAX 765-962-7170